

Produktübersicht AM-PHOTOSMART

Artikel	AM-PS1405	AM-PS3520	AM-PS5020	AM-PS6220	AM-PS7255	AM-PS7322S	AM-PS7119	AM-PS4009	AM-PS4516	AM-PS5619	AM-PS5418S	AM-PS7035	AM-PS7522
Gesamte Sonnenenergie Transmission in %	18% - 11%	24% - 19%	47% - 40%	40% - 33%	42% - 37%	30% - 19%	37% - 22%	25% - 17%	26% - 19%	29% - 21%	24% - 16%	44% - 35%	38% - 22%
Gesamte Sonnenenergie Reduktion in %	69% - 76%	66% - 70%	50% - 58%	50% - 61%	50% - 55%	61% - 77%	54% - 68%	67% - 76%	64% - 71%	62% - 68%	72% - 80%	49% - 56%	53% - 67%
Gesamte Sonnenenergie Reflektion in %	38% - 43%	36% - 37%	39% - 42%	48% - 53%	25% - 27%	60% - 65%	26% - 32%	35% - 41%	32% - 37%	24% - 29%	65% - 68%	23% - 26%	23% - 28%
Gesamte Sonnenenergie Absorbiert in %	44% - 46%	40% - 44%	13% - 17%	12% - 15%	33% - 36%	11% - 16%	37% - 46%	40% - 42%	42% - 44%	47% - 50%	11% - 16%	33% - 39%	39% - 49%
Sichtbares Licht Transmission in %	14% - 5%	35% - 20%	50% - 20%	62% - 20%	72% - 55%	73% - 22%	71% - 19%	40% - 9%	45% - 16%	56% - 19%	54% - 18%	70% - 35%	75% - 22%
Sichtbares Licht Reflektion aussen in %	22% - 26%	22% - 26%	17% - 22%	26% - 31%	12% - 13%	15% - 19%	11% - 15%	21% - 24%	19% - 21%	13% - 14%	24% - 29%	10% - 11%	10% - 14%
Sichtbares Licht Reflektion innen in %	17% - 20%	16% - 18%	15% - 16%	14% - 18%	9% - 11%	12% - 15%	11% - 14%	16% - 18%	15% - 17%	13% - 14%	15% - 18%	10% - 11%	10% - 14%
Infrarot Reduktion in %	95% - 97%	83% - 85%	63% - 67%	71% - 74%	79% - 82%	92% - 95%	93% - 94%	94% - 97%	86% - 89%	89% - 92%	99.0% - 99.5%	72% - 76%	93% - 95%
UV Reduktion in %	100% - 100%	99.8% - 99.9%	99.9% - 100%	100% - 100%	99.8% - 99.8%	99.9% - 100%	99.9% - 100%	100% - 100%	100% - 100%	99.9% - 100%	100% - 100%	99.8% - 99.9%	99.9% - 100%
Sichtbares Licht Blendungsreduzierung in %	79% - 87%	69% - 72%	50% - 69%	40% - 71%	30% - 46%	28% - 69%	30% - 63%	65% - 79%	51% - 67%	44% - 62%	45% - 70%	32% - 55%	31% - 61%
SHGC-Wert (Solar Heat Gain Coefficient)	0.30 - 0.23	0.33 - 0.31	0.46 - 0.41	0.45 - 0.39	0.49 - 0.44	0.35 - 0.26	0.46 - 0.33	0.33 - 0.24	0.36 - 0.30	0.39 - 0.32	0.32 - 0.24	0.50 - 0.43	0.47 - 0.33
Abschattung	0.34 - 0.26	0.38 - 0.36	0.52 - 0.47	0.52 - 0.44	0.54 - 0.50	0.40 - 0.30	0.53 - 0.38	0.38 - 0.29	0.42 - 0.35	0.45 - 0.37	0.37 - 0.28	0.57 - 0.49	0.54 - 0.38
Wärmeleitfähigkeit	0.19	0.19	0.2	0.2	0.2	0.19	0.2	0.19	0.19	0.19	0.19	0.2	0.2
Glanz	0.84	0.84	0.84	0.84	0.84	0.84	0.84	0.84	0.84	0.84	0.84	0.84	0.84
U - Faktor	1.05	1.03	1.05	1.03	1.06	1.03	1.06	1.05	1.05	1.05	1.03	1.06	1.06
Stärke	0,127 mm	0,063 mm	0,063 mm	0,063 mm	0,063 mm	0,093 mm	0,099 mm	0,109 mm	0,101 mm	0,101 mm	0,114 mm	0,076 mm	0,076 mm

Aristo Graphic Austria GmbH

Brixentaler Str. 80d
A-6300 Wörgl
www.aristographic.at

T: +43 5332 76229 - 0
info@aristographic.at

