BF PRINT02 BF PRINTO2 GLOSSY



PRINT&CUT

PRODUCT DESCRIPTION

BF PRINT02 (opaque) and BF PRINT02G (glossy) are polyurethane transparent films, printable with solvent, eco-solvent and latex inks, suitable for heat transfer on cotton fabrics, polyester and acrylic garments.

You must mirror when printing and cutting on this film.

It can be applied directly to the fabric, thus eliminating the need for any application tape.

TECHNICAL DATA



Film: PU/Polyurethane



Thickness: 50µ (±5%)



Liner: adhesive PET



Finish: BF PRINT02 opaque BF PRINTO2G glossy



Inks: solvent, eco-solvent, latex

APPLICATION STEPS

- Print mirror
- Cut 45° blade
- Weed excess material
- Apply BF MYLAR remove air bubbles
- Remove from liner
- Turn on your heat press heat to 150°C/305°F
- Place your graphic on the garment
- Press it 150°C/305°F for 10 seconds
- Wait 6/7 seconds
- Remove BF MYLAR semi-hot

PLOTTER SETTING



Cut settings: mirror



Blade: 45°



Minimum cut: 2 cm

APPLICATION



Temperature: 150°C - 305°F



Time: 10"



Liner removal: semi-hot

wait 6/7 seconds



Pressure: medium - 3,5 bar - 50 PSI



Textile: organic, synthetic, mixed

SIZES

H 50 cm	L 25 mt / 12,5 mt / 5 mt
H 75 cm	L 25 mt
H 100 cm	L 25 mt
H 150 cm	L 25 mt

Oeko-Tex Standard 100 Class I



Comply with regulation REACH n°1907/2006/EU

WASH RESISTANCE

First wash after application	wait 12 hours
Max wash temperature*	40°C / 104°F
Dry clean	×
Dryer	×

 $f{*}$ Temperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications. Rev_2021/03

follow us















