

## PRODUCT DESCRIPTION

BF PRINTNYLON is a printable opaque film. It's compatible with solvent, eco-solvent, and latex printers. Thanks to its custom formulated heat-activated adhesive, BF PRINTNYLON is ideal for applications on Nylon and other coated fibers (jackets, coats, duffle bags, umbrellas, shoes, backpacks, travel bags, lanyards, ...).

The high bonding power allows for a long-lasting application and ensures it will last over multiple wash cycles, even with small details and on more technical garments. The highly visible cut lines make this product easy to work with.

The sticky polyester carrier allows for easy weeding and allows you to re-position any details that accidentally lifted from the carrier.

## APPLICATION STEPS

- Print - do not mirror
- Cut - 45° blade
- Weed excess material
- Apply BF MYLAR - remove air bubbles
- Remove from liner
- Turn on your heat press - heat to 130°C/265°F
- Place your graphic on the shirt
- Press it - 130°C/265°F for 12 seconds
- Remove BF MYLAR - hot

## SIZES

**H 50 cm** L 25 mt / 12,5 mt / 5 mt

**H 75 cm** L 25 mt (upon request)

**H 100 cm** L 25 mt (upon request)

**H 150 cm** L 25 mt (upon request)

Oeko-Tex  
Standard 100  
Class I



Comply with  
regulation REACH  
n°1907/2006/EU

## SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

Rev\_2021/03

## TECHNICAL DATA



Film: PU/polyurethane



Thickness: 75µ (±5%)



Liner: adhesive PET



Finish: matte



Inks: solvent, eco-solvent, latex

## PLOTTER SETTING



Cut settings: do not mirror



Blade: 45°



Minimum cut: 0,5 cm

## APPLICATION



Temperature: 130°C - 265°F



Time: 12''



Liner removal: hot



Pressure: medium - 3,5 bar - 50 PSI



Textile: nylon, synthetic,  
faux leather, treated fabrics

## WASH RESISTANCE

First wash after application

wait 12 hours

Max wash temperature\*

40°C - 104°F

Dry clean



Dryer



\*Temperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

follow us

HEADQUARTERS B-FLEX ITALIA S.r.L. info@b-flexitalia.com | www.b-flexitalia.com

NORTH AMERICA BRANCH B-FLEX AMERICA LLC info@b-flexamerica.com | www.b-flexamerica.com

ASIA-PACIFIC BRANCH B-FLEX PACIFIC PTY LTD info@b-flexpacific.com | www.b-flexpacific.com



**BF PRINTNYLON**

**PRINT&CUT**



- Application on treated fabrics
- Strong adhesive to last over time
- Ability to cut small details