BF PRINTFLOCK

PRINT&CUT



PRODUCT DESCRIPTION

BF PRINTFLOCK is a printable heat transfer vinyl for solvent and eco-solvent inks with a flocked finish, which gives it a velvet effect that is soft to the touch and pleasing to the eye

The paper support facilitates the weeding process. After cutting and weeding, the product can be placed on the garment by taking it with the BF MYLAR, which must then be removed hot or with manual withdrawal.

It is recommended to let it dry for 8 hours before cutting.

APPLICATION STEPS

- Print do not mirror
- Cut 60° blade
- Weed excess material
- Apply BF MYLAR remove air bubbles
- Remove from liner
- Turn on your heat press heat to 160°C/320°F
- Place your graphic on the shirt
- Press it 160°C/320°F for 16 seconds
- Remove BF MYLAR hot

SIZES

| H 50 cm | L 10 mt / 5 mt / 2,5 mt | |
|----------|-------------------------|--|
| H 75 cm | / | |
| H 100 cm | / | |
| H 150 cm | / | |

TECHNICAL DATA



Film: Rayon



Thickness: ~500μ (±5%)



Liner: paper



Finish: velvet



Inks: solvent, eco-solvent

PLOTTER SETTING



Cut settings: do not mirror



Blade: 60°



Minimum cut: 1 cm

APPLICATION



Temperature: 160°C - 320°F



Time: 16"



Liner removal: hot



Pressure: medium-low - 2,0 bar - 30 PSI



Textile: organic, synthetic, mixed

WASH RESISTANCE

| First wash after application | wait 12 hours |
|------------------------------|---------------|
| Max wash temperature* | 40°C - 104°F |
| Dry clean | × |
| Dryer | × |

stTemperatures related on heat transfer vinyl; for the inks features, refer to the data sheet inks producer's.

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information above mentioned in this page. Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications. Rev_2021/03

follow us













