

**B-FLEX**  
HEAT TRANSFER VINYL

**B-FLEX**  
HEAT TRANSFER VINYL

**B-FLEX ITALIA S.r.l.**

Via 1° Maggio, 44  
36050 Sovizzo (VI) ITALY  
Ph +39 0444.028139  
info@b-flexitalia.com

**[www.b-flexitalia.com](http://www.b-flexitalia.com)**

follow us on



**BF PRINT02**



# BF PRINT02

## PRODUCT DESCRIPTION

BFPRINT02 is a polyurethane transparent film, printable with solvent, eco-solvent and latex inks, suitable for heat transfer on cotton fabrics, polyester and acrylic garments.

Thanks to its self-adhesive PET film carrier small letters and logos can be easily cut by all current cutting plotters after the printing process.

## APPLICATION INSTRUCTIONS

- Print BF PRINT 02 in way
- Wait at least 8 hours after printing, before proceeding cut.
- Cut BF PRINT 02 with a laser 45 ° blade.
- Weed the FIVE BFPRINT 02 and remove the excess materials.
- Place the BF MYLAR film on the graphic and remove the air bubbles
- Take off the graphic from the polyester backing
- Pre-heat your press to 150 ° C.
- Place the garment on the lower platen of your heat press.
- Place your BF PRINT 02 design on the garment.
- Press at 150 ° C for 10 seconds.
- Peel the BF MYLAR.

## STANDARD SIZES

- H 150 cm => available lengths: (upon request)
- H 100 cm => available lengths: (upon request)
- H 75 cm => available lengths: (upon request)
- H 50 cm => available lengths: 25 mt / 12,5 mt / 5 mt / 1 mt (standard)

## APPLICATION TIPS

- Recommended fibers: organic, synthetic, mixed
- Ability to cut design as small as 2.0 cm

## TECHNICAL DATA

Film:	PU/ Polyurethane
Thickness:	80 μ (±5%)
Carrier:	PET film – self adhesive

## APPLICATION

Temperature:	150°C - 305° F
Time:	10"
Pressure:	medium – 3,5 bar – 50 PSI

## LINER REMOVAL

Warm; wait 5-7 seconds after the application

## WASH RESISTANCE

First wash:	wait 12 hours after application
Max wash Temp.:	40° C
Dry clean:	NO
Softener:	NO
Bleach:	NO
Dryer:	NO

## SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information abovementioned in this page.

Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

This spec sheet is valid for the following products:  
BF PRINT 02. Rev\_2019 / 09.