



B-FLEX ITALIA S.r.l.

Via 1° Maggio, 44
36050 Sovizzo (VI) ITALY
Ph +39 0444.028139
info@b-flexitalia.com

www.b-flexitalia.com

follow us on



BF PRINT04



BF PRINT04

PRODUCT DESCRIPTION

BFPRINT04 is a mix of polyurethane and PVC (50%+50%) white opaque film printable with solvent, eco-solvent and latex inks.

BFPRINT04 is suitable for heat transfer on cotton fabrics, polyester and acrylic garments. Thanks to its self-adhesive carrier, the film can be easily cut by all current cutting plotters after the printing process and because of its thickness can be removed and placed on all garments by hand without. Alternatively, if preferred, we suggest to use the BF MYLAR film as a transfer tape and then remove it while hot.

APPLICATION INSTRUCTIONS

- Print BF PRINT 04
- Wait at least 8 hours after printing, before proceeding cut.
- Cut BF PRINT 04 with a laser 45° blade.
- Weed the BF PRINT 04 and remove the excess material.
- Place the BF MYLAR film on the graphic and remove the air bubbles
- Take off the graphic from the polyester backing
- Pre-heat your press to 145 ° C.
- Place the garment on the lower platen of your heat press.
- Place your BF PRINT 04 design on the garment.
- Press at 145 ° C for 12 seconds.
- Peel the BF MYLAR.

STANDARD SIZES

- H 150 cm => available lengths: (upon request)
- H 100 cm => available lengths: (upon request)
- H 75 cm => available lengths: (upon request)
- H 50 cm => available lengths: 25 mt / 12,5 mt / 5 mt / 1 mt (standard)

APPLICATIONS TIPS

- Recommended fibers: organic, synthetic, mixed
- Ability to cut designs as small as 2.0 cm

TECHNICAL DATA

Film:	PU – 50% + PVC – 50%
Thickness:	160 μ (±5%)
Carrier:	PET film – self adhesive

APPLICATION

Temperature:	145°C - 295° F
Time:	12"
Pressure:	medium – 3,5 bar – 50 PSI

LINER REMOVAL

Hot

WASH RESISTANCE

First wash:	wait 12 hours after application
Max wash Temp.:	40° C
Dry clean:	NO
Softener:	NO
Bleach:	NO
Dryer:	NO

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information abovementioned in this page.

Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

This spec sheet is valid for the following products:
BF PRINT 04. Rev_2019 / 09.