

**B-FLEX**  
HEAT TRANSFER VINYL

**B-FLEX**  
HEAT TRANSFER VINYL

**B-FLEX ITALIA S.r.l.**

Via 1° Maggio, 44  
36050 Sovizzo (VI) ITALY  
Ph +39 0444.028139  
info@b-flexitalia.com

**[www.b-flexitalia.com](http://www.b-flexitalia.com)**

follow us on



**BF PRINT  
GLOW IN THE DARK**



# BF PRINTGID

## PRODUCT DESCRIPTION

BF PRINTGID is a printable polyurethane film with a photoluminescent finishing designed to make all the graphics bright in the dark.

Thanks to its self-adhesive PET film carrier even very small letters and logos can be easily cut by all current cutting plotters after the printing process.

We recommend using BF MYLAR as a transfer tape and as a protection during the heat transfer.

## APPLICATION INSTRUCTIONS

- Print BF PRINTGID
- Wait at least 8 hours after printing, before proceeding cut.
- Cut BF PRINTGID with a laser 45° blade.
- Weed the BF PRINTGID and remove the excess materials.
- Place the BF MYLAR film on the graphic and remove the air bubbles
- Take off the graphic from the polyester backing
- Pre-heat your press to 145°C.
- Place the garment on the lower platen of your press.
- Place the BF PRINTGID design on the garment.
- Press at 145°C for 12 seconds.
- Peel the BF MYLAR.

## STANDARD SIZES

- H 150 cm => available lengths:  
(upon request)
- H 100 cm => available lengths:  
(upon request)
- H 75 cm => available lengths:  
(upon request)
- H 50 cm => available lengths:  
25 mt / 12,5 mt / 5 mt / 1 mt (standard)

## APPLICATION TIPS

- Recommended fibers: organic, synthetic, mixed
- Ability to cut design as small as 2.0 cm

## TECHNICAL DATA

Film:	PU / Polyurethane
Thickness:	140 $\mu$ ( $\pm 5\%$ )
Carrier:	PET film – self adhesive

## APPLICATION

Temperature:	145°C - 295° F
Time:	12"
Pressure:	medium – 3,5 bar – 50 PSI

## LINER REMOVAL

Warm; wait 5-7 seconds after application

## WASH RESISTANCE

First wash:	wait 12 hours after application
Max wash Temp.:	40° C
Dry cleaning:	NO
Softener:	NO
Bleach:	NO
Dryer:	NO

## SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information abovementioned in this page.

Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

This spec sheet is valid for the following products:  
BF PRINTGID. Rev\_2019 / 09.