



B-FLEX ITALIA S.r.l.

Via 1° Maggio, 44
36050 Sovizzo (VI) ITALY
Ph +39 0444.028139
info@b-flexitalia.com

www.b-flexitalia.com

follow us on



BF PRINT03



BF PRINT03

PRODUCT DESCRIPTION

BFPRINT03 is a mix of polyurethane and PVC (50%+50%) white opaque film printable with solvent, eco-solvent and latex inks.

BFPRINT03 is suitable for heat transfer on cotton fabrics, polyester and acrylic garments. Thanks to its self-adhesive carrier, the film can be easily cut by all current cutting plotters after the printing process.

We recommend using BF MYLAR as a transfer tape and as a protection during the heat transfer.

APPLICATION INSTRUCTIONS

- Print BF PRINT 03
- Wait at least 8 hours after printing, before proceeding cut.
- Cut BF PRINT 03 with a laser 45° blade.
- Weed the BF PRINT 03 and remove the excess materials.
- Place the BF MYLAR film on the graphic and remove the air bubbles
- Take off the graphic from the polyester backing
- Pre-heat your press to 145°C.
- Place the garment on the lower platen of your heat press.
- Place your BF PRINT 03 design on the garment.
- Press at 145 ° C for 12 seconds.
- Peel the BF MYLAR.

STANDARD SIZES

- H 150 cm => available lengths: (upon request)
- H 100 cm => available lengths: (upon request)
- H 75 cm => available lengths: (upon request)
- H 50 cm => available lengths: 25 mt / 12,5 mt / 5 mt / 1 mt (standard)

APPLICATIONS TIPS

- Recommended fibers: organic, synthetic, mixed
- Ability to cut design as small as 2.0 cm

TECHNICAL DATA

Film:	PU – 50% + PVC – 50%
Thickness:	120 μ (±5%)
Carrier:	PET film – self adhesive

APPLICATION

Temperature:	145°C - 295° F
Time:	12"
Pressure:	medium – 3,5 bar – 50 PSI

LINER REMOVAL

Warm; wait 5-7 seconds after the application

WASH RESISTANCE

First wash:	wait 12 hours after application
Max wash Temp.:	40° C
Dry clean:	NO
Softener:	NO
Bleach:	NO
Dryer:	NO

SAFETY NOTICE

The values reported in this document are average values as tested under normal conditions in our lab. We cannot provide a guarantee regarding the information abovementioned in this page.

Due to possible variations in the production of garments, B-FLEX recommends testing the material prior to all applications.

This spec sheet is valid for the following products:
BF PRINT 03. Rev_2019 / 09.